



### Description

A Potassium Methyl Siliconate fluid supplied in concentrate form which when diluted with water as specified is used to create a chemical damp proof course in walls above ground level where an existing DPC has broken down or an orthodox DPC is missing.

### Method

Select the course to be treated - this should be at least 150mm above external ground level (BS Code of Practice 102). Unless structural considerations prevent doing so it is important that the DPC should be below the level of any timber floor. Installation should be in accordance with BS 6576:1985 Code of Practice for installation of Chemical DPC's.

### Preparatory

Expose the line of the proposed DPC by removing all external render. Lower external ground levels where necessary without affecting the structural stability of the wall. Remove skirting and fixings and put to one side if sound, to be re-fixed. Inspect associated flooring timbers and joinery for fungal decay and treat if necessary. Remove internal plaster to expose the line of the proposed DPC. Plaster should be removed to a minimum height of 1 metre or 500mm above the last visible evidence of dampness. Advise interested parties of possible inconvenience eg. neighbours with party walls. Install safety notices and advise other trades of risks.

### Installation

**Brickwork** – drill the selected course, two holes per stretcher and one hole per header to a depth two thirds the depth of the brickwork. The hole size depends on equipment used. Injection is continued until there is a continuous band of treatment on the face of the brickwork using a pressure of up to 70 psi depending on substrate.

Single skin walls 115mm are drilled from one side.

Solid 230mm walls are preferably treated from both sides but progressive drilling can be used where this is not possible. The first skin is drilled and injected before through drilling and injecting into the second skin using average time taken for the near skin.

Thicker walls can be treated using the same progressive drilling and injecting method.

Where bricks prove too dense to allow adequate penetration of fluid drilling and injecting can be carried out in the mortar course, the holes being not more than 75mm (3") apart. Check mortar course is sound. A lower pressure may be necessary for mortar course injection.

### Stonework

The treatment is generally as for brickwork although the drilling pattern may vary.

### Rubble Filled Stonework

Both skins are treated as above although from one side the holes are drilled through to the centre of the wall and injected to achieve treatment throughout its thickness.

### General

Continuity of treatment throughout the wall should be ensured irrespective of technique.

### Consumption

This will vary according to the nature and porosity of the substrate. A general guide for 9" (230mm) brickwork would be 3 litres of diluted product per linear metre run.



.....



.....



.....



.....



## Finishing Work

The insertion of a DPC only controls further vertical ingress of water ie. rising damp. The walls above the DPC level remain wet and need time to dry out. This drying out time is governed by the initial moisture content and the wall thickness. BRE Digest 163 gives a general rate of 1 months drying out time for every 25mm of wall thickness. The first decorations following treatment should be regarded as temporary and the recommended decoration at this stage is to use a trade matt emulsion paint. Final decorations should not take place for at least 12 months following DPC treatment.

When re-plastering after treatment it is essential that a correct re-plastering specification is used to prevent contamination of the new surface by residual moisture and contaminant salts in the structure. This function has to be carried out strictly in accordance with the Permagard Re-plastering specification.

## Product Data

Packaging: 4 & 25 litre containers of concentrate. Dilute for use as indicated.

## Health & Safety Precautions

Aqueous DPC in concentrate form is a corrosive fluid and should be handled with care. The diluted fluid is classified as an irritant.

Irritating to eyes and skin – Wear overalls, gloves and eye protection.

Hands and exposed skin should be washed after use and before meals.

Eyes should be copiously irrigated with clean water for 15 minutes if in contact with material and medical advice sought if symptoms persist.

Keep away from food, drink and animal feeding stuffs.

Unprotected people and animals should be kept away from the work area.

Avoid contact with plants.

Empty container completely and do not contaminate ponds, waterways etc. Dispose of container safely.

Soak up spillage immediately with absorbent material.

C.O.S.H.H. Regulations should be adhered to where applicable.

## FOR USE BY PROFESSIONAL OPERATORS ONLY

Quality  
Products

.....

Efficient  
Service

.....

Fast  
Delivery

.....

Competitive  
Prices

.....

Great  
Value

All Permagard products are of a high quality and subject to rigid quality control. The company, however, cannot govern the conditions of usage and application of its products and any warranty, written or implied covers material only. The information contained in this leaflet is given in good faith but no liability can be assumed by the Company for any damage, loss, injury or patent infringement arising from its use. With the publication of this Technical Data Sheet all previous editions are no longer valid.

## Permagard Products Limited

Chittening Industrial Estate, Avonmouth, Bristol. BS11 0YB.

Tel: 0117 9381596

Fax: 01179 381584

Web: [www.pemagard.co.uk](http://www.pemagard.co.uk)

Email: [sales@permagard.co.uk](mailto:sales@permagard.co.uk)