

Permagard Epoxy Resin Floor Coating

Description

Permagard Epoxy Resin Floor Coating is a two-part, water-based, durable, seamless finishes, which is primarily designed for general application in all areas of industry where a hard wearing coating is required. Applications include warehouses and production units, food preparation areas, laboratory-clean room environments, and any areas of maximum hygiene, such as operating theatres and breweries.

Floors become easier to clean and substantially more resistant to damage by forklift trucks, chemicals, fuels and lubricants etc. Permagard Epoxy Resin Floor Coating also provides excellent resistance to light chemical attack and do not support fungus or bacterial growth.

Permagard Epoxy Resin Floor Coating also provides a curing membrane to increase the hardness of concrete by enabling full hydration of cement. Permagard Epoxy Resin Floor Coating can be applied to new (green) concrete 7 days after being poured.

Product Benefits

- Low-odour
- Fast (overnight) curing @ 15 - 20°C
- Apply to concrete, wood, asphalt, etc
- Apply to metal in-conjunction with a compatible primer
- Slip resistant finish (when combined with an aggregate)
- Resistant to most fuels & lubricants
- Hard-wearing
- Non-Dusting
- Satin finish
- Superior colour stability
- Superior curing at low temperature
- Freeze-thaw stability

Application Areas

Permagard Epoxy Resin Floor Coating is ideal for use in the food industry E.g. dairies, breweries and bakeries where solvent based products are prohibited. The hard-wearing, chemical / oil resistant properties also make Permagard Epoxy Resin Floor Coating ideal for:

- workshops
- warehouses
- supermarkets (back of house areas)
- general light industrial usage

Preparation

New Concrete Floors: New concrete must be clean, sound, dry and fully cured and surface laitance removed preferably by enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease or other surface contaminants by enclosed shot blasting, scarification or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing. Local repairs should be carried out using Quick-fix.

Permagard Epoxy Resin Floor Coating can also be applied to existing coatings and to wood, asphalt and other cementitious screeds which should be clean and sound with an appropriate mechanical key for adhesion.

Permagard Epoxy Resin Floor Coating can act as a curing membrane to increase hardness of concrete by allowing full hydration of cement. Permagard Epoxy Resin Floor Coating can be applied to a new (green) concrete, 7 days after being poured.

Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

Mixing: Pre-mix the base component to a uniform consistency then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components have fully combined. Streaks within the mix indicate insufficient mixing. Do not add water to this product.

The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Permagard Epoxy Resin Floor Coating should always be applied in 2 coats unless being used as a primer for other floor coating systems.

Product Information

System Thickness (Dry)	45-75 Microns (Per Coat)
Solids Contents by weight	50%
Pack Size	5kg
Shelf Life	12 months
Storage	Keep out of direct sun light. Store above 15°C

Drying Times and Coverage Rates

Coverage Rate	0.2kg/m ² 25m ² per 5kg
Pot Life	Up to 1.5 hours from mixing
Recoat Time	16-24 hours
Light Traffic	24-48 hours
Heavy Traffic	24-48 hours
Full Chemical Cure	Up to 7 days

Category Guide

FeRFA Category: 1

Technical Information

The following figures are obtained from laboratory tests and our experience with this product.

Slip Resistance	Dry > 60 Wet > 25
-----------------	----------------------

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance.

Abrasion Resistance	n/a
Temperature Resistance	Tolerant of sustained temperatures up to 60°C
Chemical Resistance	Chemical Resistance to specific materials
Compressive Strength	n/a
Flexural Strength	n/a
Tensile Strength	n/a
VOC	15g/l
Life Expectancy	2-3 years plus Subjected to Industrial Traffic

Maintenance and Cleaning

Permagard Epoxy Resin Floor Coating should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising Permagard Industrial Floor Cleaner or similar with dirty water being removed. Isolated localised cleaning can be carried out using Permagard Tyre Mark Remover.. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Health and Safety

Permagard Epoxy Resin Floor Coating is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.



All Permagard products are of a high quality and subject to rigid quality control. The company, however, cannot govern the conditions of usage and application of its products and any warranty, written or implied covers material only. The information contained in this leaflet is given in good faith but no liability can be assumed by the Company for any damage, loss, injury or patent infringement arising from its use.

Permagard Products Limited Chittening Industrial Estate, Avonmouth, Bristol. BS11 0YB.
T: 0117 938 1596 W: www.pemagard.co.uk E:sales@pemagard.co.uk

