



Betofix RM

Fast repair mortar

Colour	Availability		
	Quantity per pallet	45	36
	Packaging unit	5 kg	25 kg
	Type of container	Paper bag	Paper bag
	Container code	05	25
	Art. no.		
grey	1092	■	■

Application rate Approx. 1.2 kg/m²/mm layer thickness



Range of use



- Repair of coarse concrete surfaces in areas that are not exposed to static or dynamic loads
- Repair of holes, cracks, pores, missing and broken out areas
- Levelling of concrete surfaces
- Mineral protection against the corrosion of reinforcement steel (in combination with S-Protect M, art. 0919)

Property profile

- Certified in accordance with DIN EN 1504-3
- Can be applied by spatula and felted
- Well suited to overhead working
- Low-stress and crack-free setting
- Compressive strength after 28 days > 10 N/mm²
- Freeze/thaw-resistant

Characteristic data of the product



Water requirement	4.7 - 5.0 l/25 kg
Capillary water uptake	≤ 0.5 kg/(m ² h ^{0.5})
Strength class	R2 (DIN EN 1504-3)
Reaction to fire	Class E
Compressive strength	3 hours: approx. 3 N/mm ² 24 hours: approx. 6 N/mm ² 28 days: > 10 N/mm ²
Bulk density of fresh mortar	Approx. 1.7 kg/dm ³
Maximum grain size	0.5 mm
Adhesion capacity (DIN EN 1542) (28 days)	> 0.8 N/mm ²
Consistency of the mixture	For filling

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- [Test report M 1105/4 Corrosion protection suitability test according to EN 1504-7, ibac Aachen](#)
- [Test report P 8561-1 Basic test according to loading capability class M1, Kiwa Polymer Institute](#)
- [Classification report for reaction to fire according to DIN EN 13501-1, MPA Erwitte](#)


Possible system products

- [S-Protect M \(0919\)](#)

Preparation


- **Substrate requirements**
Clean, dust-free and capable of supporting a load.
- **Substrate preparation**
Expose all steel parts, derust to a degree of purity of SA 2½
Pre-wet the substrate so that it is slightly moist.

Production of the mixture



- **Mixing**
Protection against corrosion in combination with S-Protect M (Rust Inhibitor M)
Pour 1 part per weight S-Protect M (art. 0919) in a clean container and add approx. 2.5 parts per weight of the product.
Mix thoroughly for approximately 3 minutes until the proper consistency for working has been achieved.
- **Concrete replacement**
Pour water into a clean container and add dry mortar.
Mix thoroughly and uniformly with a mixer for approx. 2 minutes until the proper consistency for working has been achieved.

Directions



- **Conditions for use**
Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C
Low temperatures increase, while high temperatures decrease the working and setting time.
- **Working time (+20 °C)**



Approx. 20 min.

Protection against corrosion in combination with S-Protect M (Rust Inhibitor M)

Apply to layers of grout with a thickness of 1 mm each making sure the entire surface is covered.

Waiting time between layers: approx. 30 minutes.

Follow-up work must be carried out wet on wet.

Concrete replacement

If necessary, apply a scratch coat with the product itself.

Dilute the product slightly before applying the product to hard-to-reach places in the form of contact sludge.

Apply the desired layer thickness and smoothen the surface.

After 15 - 30 minutes felt, rub, smoothen or texture the surface.

Tips on use

Once it has hardened, mortar must not be made workable again by adding either water or more wet mortar.

Do not mix more mortar than can be used within approx. 20 minutes.

Can be overcoated after 2-3 hours.

Protect fresh mortar surfaces for at least 2 days from too fast dehydration, frost and rain.

Notes

The mixing water must be of drinking water quality.

May contain traces of pyrite (iron sulphide).

Low chromate content in accordance with Directive 2003/53/EC.

The characteristic data of the product were calculated under laboratory conditions at 20°C and 65% relative humidity.

The product is not suited for floor surfaces outdoors.

Tools / Cleaning


Mixer, brush, filling knife, trowel, smoothing trowel, sponge float, plasterer's float



Clean tools with water while the material is still fresh.

Storage / Shelf life

If stored in an unopened container and in a dry place, the product will keep for approx. 12 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Declaration of performance

➤ **Declaration of performance**



CE marking



Remmers GmbH

Bernhard-Remmers-Str. 13, D – 49624 Lönigen

09

GBI P 3-2

EN 1504-3: 2005

1092

PCC mortar for non structural repair for concrete

Compressive strength:	Class R2
Chloride ion content:	≤ 0.05 %
Adhesive bond:	≥ 0.8 MPa
Restrained shrinkage/expansion:	≥ 0.8 MPa
Carbonation resistance:	NPD
Elastic modulus:	NPD
Thermal compatibility part 1 and 4:	≥ 0.8 MPa
Capillary absorption:	≤ 0.5 kg/(m ² h ^{0.5})
Reaction to fire:	Class E

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.