

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane



Revision: 5.3 - 12th January 2023
Code: 107F

INTRODUCTION


Newton HydroCoat 107 Elastic 2K is a two-component, cementitious, polymer-rich coating for the waterproofing and protection of concrete and masonry. Capable of withstanding heads of water pressure up to 10 bar of positive pressure and up to 1.5 bar to the negative side of the structure, HydroCoat 107 Elastic 2K is ideally suited to the waterproofing of reservoirs, tunnels, water tanks, earth-retaining structures and covered or buried decks, and is especially capable where the structure has both masonry and concrete elements where differential movement is expected.

When mixed, HydroCoat 107 Elastic 2K is thixotropic to enable ease of application by brush or airless spray, providing an even finish with no sagging and excellent adhesion to prepared concrete and masonry substrates, even in vertical and overhead situations. HydroCoat 107 Elastic 2K is reinforced over static joints and at details and changes of direction with [HydroCoat 912-RT](#).

HydroCoat 107 Elastic 2K hydrates to form a durable, highly alkaline and permanently elastomeric coating which protects concrete and other substrates from water penetration, and also accommodates slight movement in cracks and at correctly specified movement joints. The product is also supported by BDA Agrément® BAB 18-026-P-A-UK and accepted by the NHBC as a suitable waterproofing system for Type A Waterproofing to Grades 1, 2 and 3 - BS 8102:2022 and to covered decks.



APPLICATION




PROPERTIES

H - Hardness and Durability; E - Elasticity and Flexibility; V - Vapour Resistivity; C - Curing and Drying; W - Working Time; U - UV Stability



PACKAGING



A+B Components already measured, in two containers

COVERAGE



KEY BENEFITS

- Pre-packaged materials easily mixed on site
- Tough, flexible coating which maintains its elastomeric properties even when immersed
- Excellent adhesion to sound prepared concrete and masonry substrates, as well as steel
- Suitable for positive and negative waterproofing of earth-retaining structures as well as covered decks
- Dense matrix offers low permeability to water
- A 2 mm coat provides the equivalent to 135 mm of good quality concrete cover
- Can be applied to damp substrates in temperatures down to +5°C
- Water-based product. Non-toxic when cured



HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

TECHNICAL DATA


Features	Result	Units				
Form – Two components	Part A liquid + Part B powder					
Colour	Grey					
Density/Specific gravity	1.6					
Pack size	30	kg				
Yield per kg	0.63	Litres				
Shelf life	24	Months				
Pot life @ 20°C & RH of 60%	45	Minutes				
Finishing time	Within 10 minutes of placing					
Application rate – in one or two coats	3.2	kg/m ²				
Substrate application temperature	+5 to +30	°C				
Service temperature	-15 to +80	°C				
Odour	Low - Characterised as polymeric					
VOC content - Part A only (none when cured)	1.76	g/L				
Curing*	5°C	10°C	15°C	20°C	25°C	Units
Ready for next coat	8	7	6	5	3	Hours
To not be adulterated by rain	5	4	3	2.5	2	Hours
Ready for temporary traffic/protection boards	72	72	72	48	48	Hours
Ready for flood/hosepipe test	7	7	7	7	7	Days
Fully cured	28	28	28	28	28	Days
Cured Performance	Result	Units	Test Method			
Colour	Grey					
Membrane thickness in one or two coats	2.0	mm				
Adhesion to concrete	0.89	MPa	BS EN 1542			
Tensile strength - Ambient**	0.5	MPa	BS 6319-7:1994			
Tensile strength - Immersed**	0.4	MPa	BS 6319-7:1994			
Elongation at break - Ambient**	120 - 130	%	Manufacturer test			
Elongation at break - Immersed**	70 - 80	%	Manufacturer test			
Static crack bridging capability (class A5)	>2.5	mm	BS EN 1062-7 - Method A			
Dynamic crack bridging capability	1000 cycles	0.2 -0.5 mm	BS EN 1062-7 - Method B			
Compressive strength – 28 days	8 to 10	MPa	BS 4551			
Hardness	84.0	Shore A	BS EN ISO 868:2003			
Flexural Strength	3.5 – 4.0	MPa	EN196-1			
Water Permeability Coefficient	5.37 x 10 ⁻¹⁶	m/sec	DIN 1048 Part 1			
Water vapour diffusion resistance – S _d value	1.55	m	BS EN ISO 7783-2			
Water vapour diffusion resistance – μ value	775	μ	Calculation from S _d value			
Water vapour diffusion resistance	7.75	MNs/g	Calculation from S _d value			
Water resistance – Positive side	10.0	Bar	DIN 1048			
Water resistance – Negative side	1.50	Bar	DIN 1048			
Liquid Water Transmission Rate (Capillary Absorption and Permeability to Liquid water)	w = 0.0086 kg.m ⁻² .h ^{-0.5}		EN1062-3			
Permeability to CO ²	57****	m	EN 1062-6			
Thermal compatibility	0.88*****	MPa	EN 13687-1			
Water Permeability Coefficient	5.37 x 10 ⁻¹⁶ m/sec		DIN 1048			
Equivalent Concrete Thickness	2mm = 2270mm of concrete					
Reaction to fire classification - Euroclass	B - s1, d0		BS EN 13501-1			
UV Resistance - Stable but will discolour	50	Years	UNI EN ISO 11507:2007***			
Root Resistance	Barrier to Root Penetration (Lupin Test)		DD CENT/TS 14416			
pH	12					

The above data, even if carried out according to regulated tests are indicative and they may change when specific site conditions vary. *Figures are influenced by humidity also and so are indicative. **2mm film cured for 28 days. ***UNI EN ISO 11507:2007 is an accelerated ageing test. The result of 1000 hours translates to 50-years. ****2mm equivalent to 135mm of concrete. ***** Crack bridging flexible systems without trafficking

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

TYPICAL DETAIL



TYPICAL APPLICATIONS

Waterproofing of:

- Podium decks, flat roofs, terraces and balconies
- Water-retaining structures such as water tanks and reservoirs
- Earth-retaining foundation walls to both the positive and negative side
- Internal concrete surfaces of walls and rafts or slabs to earth-retained structures such as habitable basements, car parks, plant rooms and lift-pits

ACCREDITATIONS & APPROVALS

HydroCoat 107 Elastic 2K is independently tested by BSI to confirm performance data to the requirements of EN 1504-2:2004 in accordance with the EU Construction Products Regulations. Please see CE Label on page 7, or the product [Declaration of Performance](#) for further information.

HydroCoat 107 Elastic 2K is supported by KIWA BDA Agrément and is accepted by the NHBC as a suitable waterproofing system for Type A Waterproofing to Grades 1a, 1b, 2 & 3 - BS 8102:2022, and for the waterproofing of covered decks, both as standalone product or in conjunction with other approved products that form the overall waterproofing specification.

*Bond to abraded steel is very good but not tested and so is suitable only for termination detailing

SUITABLE SUBSTRATES

Correctly prepared substrates of:

- Concrete of at least 20kN
- Steel*
- Structural masonry/mortar
- Screed

SUITABLE SURFACES

Waterproofing of:

- Walls - Positive pressure and Negative pressure
- Slab/raft - Negative pressure
- Soffit - Negative pressure
- Deck - Positive pressure

METHOD OF APPLICATION

- Squeegee
- Roller
- Airless Spray
- Pin Leveller
- Brush
- Trowel

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

SPECIALIST TOOLS REQUIRED

- Spiked shoes and spiked roller to ensure captured air is removed and to improve the surface finish
- To spray the product, an airless machine is required

SPECIFICATION

Newton Waterproofing Systems work in partnership with RIBA NBS who publish our products on [NBS Source](#). The platform integrates seamlessly into project workflows, providing all product data from Newton's NBS BIM Objects, NBS Plus Clauses and RIBA Product Selector into one single source of product information.

NBS Source also hosts a large selection of Newton [case studies](#), as well as product [literature and certifications](#).

A wide range of drawings are available [on our website](#).

TRAINING AND COMPETENCY OF THE USER

HydroCoat 107 Elastic 2K should only be used by those with an understanding of the requirement to waterproof retained structures and the knowledge and training to use the product as part of a coordinated approach to the waterproofing of the structure, which in many cases will require further waterproofing products so as to achieve the required habitable grade as defined by BS 8102:2022.

It is recommended that HydroCoat 107 Elastic 2K and its ancillary products be installed by contractors trained by Newton Waterproofing Systems in the correct use and specification of the product.

PROTECTION OF THE MEMBRANE

The membrane is not wear resistant and requires protection from wear and weathering.

Protection methods include:

- Decks - Newton drainage membrane, [NewSeal 408 DeckDrain](#), with paving or Intensive Green Roof over
- Decks - [NewSeal 420 DeckDrain](#) drainage and water storage membrane with Extensive Green Roof over
- Decks - Timber decking
- Decks - Paving on pedestals
- Decks & internal floors - Coloured sands or grit 100% broadcasted to the still tacky final coat to provide an abrasion and slip resistant finish.
- Decks - Ceramic tiling adhered directly to 100% broadcast with sand surface. Waterproof grout and waterproof adhesives to be used.
- Internal floors - Ceramic tiling adhered to a de-coupling membrane
- Internal Floors - Screed or other floor coverings
- External walls - [Hydrobond 410 GeoDrain](#), [CDM Fibran XPS 500C](#) insulation or protection board

LIFE EXPECTANCY

When specified, installed and protected in accordance with the Data Sheet, fully and permanently isolated from UV light and physical damage or wearing, and only to those substrates confirmed within, HydroCoat 107 Elastic 2K has a service life that can be equal to the design life of the structure.

HydroCoat 107 Elastic 2K is guaranteed to resist weathering for up to 10-years. The membrane is not UV colour stable and will slightly fade in colour over time, and it may take a few months for the colour to be consistent. Over time discolouration due to weathering may take place, but the membrane will be serviceable.

The membrane is not hard wearing and should be protected against wear.



PACKAGING

The product consists of two parts, A and B, both of which are measured and ready to be mixed:

- Part A (Container of liquid) 10 kg
- Part B (Bag of powder) 20 kg

APPLICATION RATE

The membrane is applied to a total thickness of 2.0 mm, which requires an application rate of 3.2 kg/m².

Walls and soffits

Application is by two coats, each of 1.6 kg/m².

Horizontal surfaces

Application is by two coats, each of 1.6 kg/m² or by a single coat of 3.2 kg/m².

At a thickness of 2.0 mm, a 30kg composite pack covers a total surface area of 9.4m².

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

ANCILLARY PRODUCTS

- [HydroCoat 903 Primer](#) - Purchase Code 903-P. Primer for concrete
- [HydroCoat 905-CM](#) - Purchase Code 905-CM. Curing membrane to prevent accelerated drying during hot or very windy conditions
- [HydroCoat 912-RT](#) - Purchase Code 912-RT. Reinforcement Tape for static joints construction joints

CONSTRUCTION

The construction should conform with current Building Regulations, British Standards and Codes of Practice.

CONSTRUCTION - NEW CONCRETE

New concrete to earth retaining structures should be designed by a Structural Engineer to EN 1992 (Formerly BS 8110). A shuttered finish to vertical surfaces is suitable for HydroCoat 107 Elastic 2K.

Horizontal concrete surfaces should have a surface finish to at least Class of finish U3 and preferably to class U4 or U5 as documented in 'General Specification for Civil Engineering Works' section 14: 'Formwork and Finishes to Concrete', namely a 'Uniform, dense and smooth surface'. Float marks should be avoided as these will impact on the cost of correct surface preparation.

HydroCoat 107 Elastic 2K can be applied to new concrete providing that:

- The concrete is at least 20 N strong
- The concrete can be prepared using conventional mechanical preparation methods to remove laitance to floors and release agents to walls

CONSTRUCTION - MORTAR

Walls should be designed by a Structural Engineer to withstand the load of the retained earth as well as the expected water pressure as defined by BS 8102:2022. The mortar joints should be pointed flush to the surface of the wall.

SURFACE PREPARATION - GENERAL

Generally the surfaces to be waterproofed must be structurally stable, clean, dry and free from release agents, dust, laitance, oils, paints or other forms of contamination.

Substrate damage, deterioration, cracks, voids, and holes should be repaired and filled prior to installation of the waterproof membrane with HydroCoat 203-RM repair mortar. Deep or structural cracks should be inspected to confirm if they are live or dormant. Suitable repair by qualified personnel is recommended.

SURFACE PREPARATION - CONCRETE WALLS

Jet washing with minimum pressure of 2500 PSI should be used to remove release agents and surface contamination to concrete walls. Adding mild detergents to the jet wash water will improve effectiveness.

Fine surface cracks and blow-holes should be filled with sand/cement using a bag rubbing technique.

Tie-Bolt holes should be filled with HydroCoat 203-RM.

SURFACE PREPARATION - MORTAR WALLS

Joints should be flush pointed. If they are not, re-point or apply a smoothing coat of sand/cement render with [HydroCoat 908-LB](#) mixed into the gauging water at 1:2.

Porous block walls should be filled by bag-rubbing with sand/cement.

Existing walls of block or brick will require wall surface preparation such as grit blasting or scabbling to ensure all surface containments are removed and that a good 'key' is achieved. Remove snots.

SURFACE PREPARATION - CONCRETE FLOORS

In all cases, concrete floors should be ground or sand blasted to remove laitance. Vacuum clean after.

If the concrete floor needs to be levelled, please speak to the Newton Waterproofing Technical Department who will advise on the correct levelling product.

Large holes or indentations should be filled [HydroCoat 203-RM](#).

SURFACE PREPARATION - METAL

Clean to remove surface contaminants and abrade to a slightly textured finish.

JOINTS & CHANGES OF DIRECTION

Reinforce static joints with HydroCoat 912-RT.

Over shrinkage joints, use 25mm wide masking tape to create delamination. With movement joints, lap the HydroCoat 107 Elastic 2K into the joint and then use our standard [FlexProof 106](#) movement joint detail. Please speak to our Technical Department for assistance on the correct specification to joints.

PRIMING

Walls and soffits - Prior to slurry tanking, porous substrates should be sealed with sand/cement using a bag rubbing technique.

Internal slabs and rafts - Porous substrates should be sealed with HydroCoat 903-P.

External decks - Prime with HydroCoat-P.

Please read the HydroCoat 903-P data sheet before commencement of application.

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

MIXING

Newton Waterproofing supply the full range of [Collomix Mixing Equipment](#) that includes Hand Mixers, Stirrers, Mixing Stands, Buckets, Transport Carts and the Mixer Clean mixing bucket. HydroCoat 107 Elastic 2K can be mixed with the DLX (preferred) and KR stirrers, matched to the Xo 1 or Xo 4 Hand Mixers which are suitable for quantities of up to 65 litres. For larger quantities the MKD dual action stirrer is matched to the Xo 55 duo Hand-Mixer.

- Shake Part A bottle thoroughly and pour into clean mixing vessel
- Add part B (powder) slowly whilst mixing slowly
- Mix for 5 minutes until smooth, entrapping as little air as possible
- Continuously scrape sides to prevent lumps forming and to ensure all of part A is mixed with all of part B
- Mix for a minimum of 5 minutes and use without delay



APPLICATION

The mixed slurry can be applied by Brush, Squeegee, Roller, Trowel or Pin Leveller. Ensure that air is not entrapped into the surface of horizontal applications by using a spiked roller as soon as the product is placed.

With two coat applications, the second coat can be applied when the first coat is still 'green' and slightly tacky and up to five days after the first coat has been applied. After five days, the first coat will need to be washed to remove dust. A primer of HydroCoat 908 LiquaBond mixed 1:1 with water can be applied to enhance adhesion of the second coat to the first.

SPRAYING SPECIFICATION

HydroCoat 107 Elastic 2K can be sprayed with an airless spray machine. For information on the machine and configuration, please contact our Training Department.

CURING

For curing/drying times please see Technical Data on page 2. HydroCoat 107 Elastic 2K is a cement-based product and so requires curing. Accelerated drying must be avoided.

If the conditions are hot, sunny and/or very windy the finished membrane must be protected from accelerated drying with the application of HydroCoat 905-CM, a simple to apply liquid curing membrane.

In floor and deck applications, coloured sands or grit can be cast liberally onto the surface to provide effective curing, whilst also creating an abrasion and slip-resistant finish.

Curing must commence within 10-15 minutes of the completed application of the coating.

POT LIFE & FURTHER USE

HydroCoat 107 Elastic 2K is a two-part product and a chemical curing reaction starts as soon as the two parts are mixed. Pot life is 45 minutes at 20°C. Product must be used before it starts to go off/over thicken.

CLEANING

Thoroughly clean all tools and equipment with water immediately after use.

LIMITATIONS

- Do not apply prior to rain - please see information within the curing table on page 2
- Do not apply at temperatures lower than +5°C or higher than +30°C
- Always use the correct preparation and priming of the support substrate as directed above

COLOUR

Grey.

STORAGE

Store in dry conditions at temperatures between +5°C and +25°C with containers fully sealed. Do not expose to freezing conditions.

If these conditions are maintained and the product packaging is unopened, then a shelf life of up to 24 months can be expected.

Please note: The sacks are splash proof and not waterproof. Please ensure that the product is moved to dry site storage as soon as it is delivered.

HEALTH & SAFETY

Use appropriate PPE for the environment the system is installed within. Use products only as stated within this Data Sheet and the SDS.

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

CHEMICAL RESISTANCE

THE EFFECT OF VARIOUS CHEMICALS ON THE PROPERTIES OF HYDROCOAT 107 ELASTIC 2K

2mm thick films of HydroCoat 107 Elastic 2K were cast and cured for 28 days at 20°C/65% RH before being cut into test pieces of 30 x 90mm. The test pieces were measured accurately and immersed in the solutions/chemicals of the table below at 20°C.

3 test samples were removed from each solution at 28 days and a further 3 were removed at 3 months. After removal the samples were measured and tested for tensile strength under elongation using a Lloyd Instruments Tensometer.

The performance of HydroCoat 107 Elastic 2K in each test liquid / solution was evaluated and given a rating in each case which takes into account (i) surface condition and (ii) overall performance in the particular medium. This ranges from 0 to 10 where 0 represents total disintegration of the sample and 10 represents perfect surface condition and no decrease in performance relative to control samples which were cured at 20°C and 65% RH for the test period.

RESULTS

See table below.



CONCLUSION

Although the overall chemical resistance of HydroCoat 107 Elastic 2K is as good as normal concrete, for high demand applications HydroCoat 103 2K should be used (please consult the chemical table on page 7 of the HydroCoat 103 2K TDS)

TEST MEDIUM	1 MONTH IMMERSION				3 MONTHS IMMERSION			
	VOLUME CHANGE (%)	TENSILE STRENGTH (N/mm ²)	% OF CONTROL STRENGTH	RATING (/10)	VOLUME CHANGE (%)	TENSILE STRENGTH (N/mm ²)	% OF CONTROL STRENGTH	RATING (/10)
(AIR CURE)	-2.3	0.434	-	10	-1.6	0.695	-	10
DEIONISED WATER	+6.5	0.363	83.6	9	+16.0	0.458	65.8	8
SYNTHETIC SILAGE	+13.0	0.193	44.5	5	+46.4	0.056	8.0	1
MAGNESIUM SULPHATE SOLUTION	+33.8	0.305	70.2	7	+40.0	0.236	33.9	3
AMMONIUM NITRATE SOLUTION	+18.2	0.150	34.6	4	+16.1	0.095	13.7	2
FERROUS SULPHATE SOLUTION	+33.6	0.461	106.2	10	+79.4	0.397	57.1	5
AMMONIUM SULPHATE SOLUTION	+73.6	0.088	20.2	2	+76.7	0.049	7.1	1
ACETIC ACID	+46.0	0.056	12.9	2	+9.1	0.066	9.5	2
HYDROCHLORIC ACID	+38.0	0.047	10.8	2	+65.9	-	-	0 (TOTAL DISINTEGRATION)
SULPHURIC ACID	+102.8	0.043	9.9	1	+100.1	0.040	5.7	1
METHANOL	+44.4	0.275	63.4	6	+8.4	0.432	62.2	7
SODIUM HYDROXIDE SOLUTION	+76.7	0.084	19.4	2	-	-	-	0 (TOTAL DISINTEGRATION)
SODIUM HYPOCHLORITE SOLUTION	+11.1	0.413	95.2	10	+1.1	0.356	51.1	6
TRANSFORMER OIL	+56.6	0.172	39.6	4	+46.6	0.257	37.0	4
DIESEL	+79.2	0.120	27.6	2	+80.0	0.163	23.4	2
PARAFFIN	+55.5	0.130	30.0	3	+82.3	0.128	18.4	2
SKYDROL	+59.8	0.117	27.0	3	+26.8	0.132	19.1	2
PETROL	+146.6	0.053	12.2	1	+265.8	0.046	6.7	1

HydroCoat 107 Elastic 2K

Cementitious Flexible Waterproofing Membrane

				Newton Waterproofing Systems Newton House 17-20 Sovereign Way Tonbridge Kent TN9 1RH		107F EN 1504-2:2004 0086 / 0833 Surface Protection System for Concrete	
Essential Characteristics	Declared Performance	Test Standard	Harmonised Technical Standard				
Permeability to CO ²	Equivalent to 135mm of concrete	BS EN 1062-6	BS EN 1504-2				
Permeability to water vapour	SD <5m Class I Permeable to water vapour	BS EN ISO 7783-2					
Capillary absorption	<0.1kgm ⁻² h ^{-0.5} Class III	BS EN 1062-3					
Adhesive bond	≥ 0.8 MPa	BS EN 1542					
Thermal compatibility	> 0.8 MPa	BS EN 13687-1					
Dangerous substances	Complies	Clause 5.4					
Reaction to fire	Euroclass B - s1, d0	BS EN 13501-1					
Cracking bridging - Static	> 2500µm - Class A5	BS EN 1062-7					
Cracking bridging - Dynamic	200-500 µm - Class 4.1	BS EN 1062-7					

Any specification/advice provided is only valid if used with products supplied by John Newton and Company Ltd (trading as Newton Waterproofing Systems). Newton Waterproofing Systems reserve the right to update product literature at any time. Please always refer to our [website](#) for the latest versions.