

PermaCOAT **PRO**

High Build Epoxy Floor Coating Non-Slip



PermaCOAT PRO High Build Epoxy Floor Non-Slip Coating is a two-pack solvent free, high build epoxy resin coating for application as a heavy duty coating at a thickness of 200 to 500 microns. The coloured high gloss finish is extremely hard wearing and has good general chemical resistance.

PermaCOAT PRO High Build Epoxy Floor Non-Slip Coating has a low-odour during application and provides a sealed, continuous and hygienic floor surface when cured.

Our Epoxy Floor Coating HB is easily applied and provides a tough, resilient, corrosion and abrasion resistant finish. Anti-slip finishes can be achieved by the inclusion of aggregates.

Floors become easier to clean and substantially more resistant to damage by forklift trucks, chemicals, fuels and lubricants etc.

PermaCOAT PRO High Build Epoxy Floor Non-Slip Coating also provides excellent resistance to light chemical attack and does not support fungus or bacterial growth.

APPLICATION AREAS

PermaCOAT PRO High Build Epoxy Floor Non-Slip Coating is ideal for use in the food industry e.g. dairies, breweries and bakeries where solvent based products are prohibited.

The hard-wearing, chemical/oil resistant properties also make Permagard Epoxy Floor Coating ideal for:

- Workshops/ garages
- Warehouses
- Supermarkets (back of house areas)
- General light industrial usage

PermaCOAT PRO HIGH BUILD EPOXY FLOOR COATING	PRODUCT & TECHNICAL INFORMATION
System Thickness (Dry)	200-500 microns (per coat)
Solids Contents by Weight	100%
Pack Size	5kg + 250g aggregate
Shelf Life	12 months
Storage	Keep out of direct sunlight. Store above 15°C
Abrasion Resistance	n/a
Temperature Resistance	Tolerant of sustained temperatures up to 45°C
Chemical Resistance	Good resistance to specific materials
VOC	197g/l
Life Expectancy	3-4 years plus. Subjected to industrial traffic.
Category	FeRFA Category: 2
Slip Resistance*	Dry > 60 Wet > 25

* The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance.

PermaCOAT PRO HIGH BUILD EPOXY FLOOR COATING	DRYING TIME & COVERAGE RATES
Coverage Rate	0.25kg/m ² 20m ² per 5kg
Pot Life	Up to 25 mins from mixing
Recoat Time	6 hours or once surface has lost tackiness
Light Traffic	12 to 16 hours
Heavy Traffic	24 to 36 hours
Full Chemical Cure	Up to 7 days

PREPARATION, PRIMING, MIXING & APPLICATION

PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry and fully cured and surface laitance removed preferably by enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease or other surface contaminants by enclosed shot blasting, scarification or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing. Local repairs should be carried out using PermaCOAT Epoxy Repair Mortar and PermaCOAT Epoxy Crack Filler. PermaCOAT PRO High Build Epoxy Floor Coating can also be applied to existing coatings and to wood, asphalt and other cementitious screeds which should be clean and sound with an appropriate mechanical key for adhesion.

PRIMING

Porous substrates may require priming with PermaCOAT Epoxy Floor Coating or PermaCOAT Epoxy Primer. Damp surfaces should be treated with one of the PermaCOAT Epoxy Damp Proof Membranes.

MIXING

Pre-mix the base component to a uniform consistency then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components are fully combined. Streaks within the mix indicate insufficient mixing. Do not add water to this product. For the non-slip version, add the pot of aggregate to the base and hardener mix and continue to mix until the aggregate is evenly spread throughout. The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks. On larger areas it is imperative that the same batch numbered product is used across the whole floor.

APPLICATION

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

BENEFITS

- High build coatings are obtainable in one application
- Hygienic and easy to clean and maintain
- Good colour stability
- Suitable for application where a bacteria-free finish is important
- Aggregates can be incorporated for improved slip and abrasion resistance and wearing properties
- Excellent high gloss finish
- No shrinkage on curing
- Light duty, non-slip finish

The HB (high build) version of our Epoxy Floor Coating has a higher solid content level than our standard Epoxy Floor Coating. When applied to a surface this gives a dry coat thickness nearly three times the thickness of the standard product. This provides a more substantial coating creating a tough, resilient, corrosion and abrasion resistant finish which is longer lasting.

Application Notes: PermaCOAT PRO High Build Epoxy Floor Coating should not be applied in areas of intense UV exposure as the product may discolour over a period of time. Please speak to our technical department for further information.

MAINTENANCE AND CLEANING

PermaCOAT PRO High Build Epoxy Floor Coating should be cleaned with a regular industrial cleaning regime with a floor scrubber. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

HEALTH AND SAFETY

PermaCOAT PRO High Build Epoxy Floor Coating is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

For further information please see latest safety data sheet.

All Permagard products are of a high quality and subject to rigid quality control. The company, however, cannot govern the conditions of the usage and application of its products and any warranty, written or implied covers material only. The information contained in this leaflet is given in good faith but no liability can be assumed by the Company for any damage, loss, injury or patent infringement arising from its use.

Permagard Products Ltd
Units B2-B5, Worthy Road
Chittening Industrial Estate
Avonmouth, Bristol, BS11 0YB